

# ステンレス板SUS304 (2B)

(0.8tより切断売り)

(単位m/m)

JIS 規格名及記号 G4305 G4307 SUS304-CP, SP  
 配 合 (%) Ni 8.0~10.5 Cr18.0~20.0  
 C10.08以下 Si1.0以下 Mn2.0 以下  
 Po0.045 以下 S 0.03以下  
 仕 上 げ 2B  
 比 重 7.93

板 厚 公 差	0.3 以上 0.6未満	±0.05
	0.6 " 0.8 "	±0.07
	0.8 " 1.0 "	±0.09
	1.0 " 1.25 "	±0.10
	1.25 " 1.6 "	±0.12
	1.6 " 2.0 "	±0.15
	2.0 " 2.5 "	±0.17
	2.5 " 3.15 "	±0.22
	3.15 " 4.0 "	±0.25
	4.0 " 5.0 "	±0.35
5.0 " 6.0 "	±0.40	
6.0 " 8.0 "	±0.50	

厚 さ mm	幅 mm	長 さ mm	仕上げ	1 枚 重量 kg	無 計 量 採 用	備 考
0.3	1,000	2,000	2 B	4.76	○	2.0tより薄 い物はシャ ーリング切 断になります。 す。
0.4	"	"	"	6.34	○	
0.5	"	"	"	7.93	○	
0.6	"	"	"	9.52	○	
0.8	"	"	"	12.70	○	
1.0	"	"	"	15.90	○	
1.2	"	"	"	19.00	○	
1.5	"	"	"	23.80	○	
2.0	"	"	"	31.70	○	
2.5	"	"	"	39.60	○	
3.0	"	"	"	47.60	○	
4.0	"	"	"	63.40	○	
5.0	"	"	"	79.30	○	
6.0	"	"	"	95.20	○	
4 × 8 板						
0.8				18.90	○	
1.0	1,219	2,438	2 B	23.60	○	
1.2	"	"	"	28.30	○	
1.5	"	"	"	35.40	○	
2.0	"	"	"	47.10	○	
2.5	"	"	"	58.90	○	
3.0	"	"	"	70.70	○	

○印は無計量採用寸法です。

一口メモ 表面仕上げの2Bとは冷間圧延後、熱処理、酸洗又はこれに準ずる処理を施したのち、  
 適当な光沢を得る程度に冷間圧延して仕上げたものです。