

# ステンレス板 SUS 316 (No.1) 切断板

(切 断 売 り)

JIS 規格名及記号 G4304 SUS316-HP

配 合 (%) Ni 10.0~14.0 Cr 16.0~18.0

Mo 2.0~3.0 C 0.08以下 Si 1.0以下

Mn 2.0以下 P 0.04以下 S 0.03以下

仕 上 げ No.1  
比 重 7.93

(単位m/m)

板 厚 公 差	2.5 以上 3.15未満	±0.35
	3.15 " 4.0 "	±0.40
	4.0 " 5.0 "	±0.45
	5.0 " 6.0 "	±0.50
	6.0 " 8.0 "	±0.60
	8.0 " 10.0 "	±0.65

厚 さ mm	元 板		1 枚 重 量 kg	備 考
	幅 mm	長さ mm		
3.0	1,525	3,050	110.00	
4.0	"	"	148.50	
5.0	"	"	185.58	
6.0	"	"	222.70	
8.0	"	"	297.00	
9.0	"	"	334.05	
10.0	"	"	371.17	
12.0	"	"	445.40	
14.0	"	"	519.64	
15.0	"	"	556.75	
16.0	"	"	593.87	
18.0	"	"	668.11	
19.0	"	"	705.22	
20.0	"	"	742.34	
22.0	"	"	816.57	
25.0	"	"	927.92	
28.0	"	"	1,039.28	
30.0	"	"	1,113.51	
32.0	"	"	1,187.74	
35.0	"	"	1,299.09	
38.0	"	"	1,410.45	
40.0	"	"	1,484.68	
45.0	"	"	1,670.26	
50.0	"	"	1,855.85	
55.0	"	"	2,041.43	
60.0	"	"	2,227.02	
65.0	"	"	2,412.60	
70.0	"	"	2,598.19	
75.0	"	"	2,783.77	
80.0	"	"	2,969.36	
85.0	"	"	3,154.94	
90.0	"	"	3,340.53	
95.0	"	"	3,526.11	
100.0	"	"	3,711.70	

一口メモ SUS316はMoの添加により希硫酸、亜硫酸に対する耐食性がSUS304より優れている。又、高温強度も大である。用途石油化学工業、食品工業 etc.