

# ステンレス丸棒 SUS303 (快削) (ピーリング)

JIS 規格名及記号 G4303 SUS303 ステンレス鋼

配合 (%) C 0.15以下 Si 1.00以下

Mn 2.00以下 P 0.20以下 S 0.15以下

Ni 8.00~10.00 Cr 17.00~19.00

(単位: m/m)

仕 上 げ 酸洗及びピーリング  
比 重 7.93

径	外径公差	長さ公差
28φ以下	±0.4	乱尺
30φ~	±1.5%	"

径 mm	長 さ mm	1 m 当り重量 kg	表 面 仕 上	切 断 可 否	無計量 採 用	備 考
8	4,200	0.398	ピーリング	否	○	
9	"	0.504	"	"	○	
10	"	0.623	"	可	○	
11	"	0.753	"	"	○	
12	"	0.896	"	"	○	
13	"	1.052	"	"	○	
14	"	1.220	"	"	○	
15	"	1.401	"	"	○	
16	"	1.594	"	"	○	
17	"	1.799	"	"	○	
18	"	2.017	"	"	○	
19	"	2.247	"	"	○	
20	"	2.49	"	"	×	
22	"	3.01	"	"	×	
24	"	3.59	"	"	×	
25	5.5m 乱尺	3.89	"	"	×	
26	"	4.21	"	"	×	
27	"	4.54	"	"	×	
28	"	4.88	"	"	×	
30	"	5.61	"	"	×	
32	"	6.38	"	"	×	
34	"	7.20	"	"	×	
35	"	7.63	"	"	×	
36	"	8.07	"	"	×	
38	"	8.99	"	"	×	
40	"	9.97	"	"	×	
42	"	11.0	"	"	×	
45	"	12.6	"	"	×	
46	"	13.2	"	"	×	
48	"	14.4	"	"	×	
50	"	15.6	"	"	×	
55	"	18.8	"	"	×	
60	"	22.4	"	"	×	
65	"	26.3	"	"	×	

×印は計量する寸法です。

一口メモ SUS303は快削ステンレスの代表鋼種でSUS304に少量のサルファーを添加したものです。  
材質識別の為両端面にピンクのスプレーをしております。

# ステンレス丸棒SUS303 (快削)

(切断売り)

径 mm	長さ mm	1 m 当り参考 重量 kg	表面 仕上	切断 可否	無計 採用	備考
70	5.5m乱尺	30.5	ピーリング	可	×	
75	〃	35.0	〃	〃	×	
80	〃	39.9	〃	〃	×	
85	〃	45.0	〃	〃	×	
90	〃	50.4	〃	〃	×	
95	〃	56.2	〃	〃	×	
100	〃	62.3	〃	〃	×	
105	〃	68.7	〃	〃	×	
110	〃	75.4	〃	〃	×	
115	〃	82.4	〃	〃	×	
120	〃	89.7	〃	〃	×	
125	〃	97.3	〃	〃	×	
130	〃	105.3	〃	〃	×	
135	〃	113.5	〃	〃	×	
140	〃	122.1	〃	〃	×	
145	〃	130.9	〃	〃	×	
150	〃	140.1	〃	〃	×	
160	4m~5m乱尺	159.4	〃	〃	×	
170	〃	180.0	〃	〃	×	
180	〃	201.8	〃	〃	×	
190	〃	227.0	〃	〃	×	
200	〃	249.1	〃	〃	×	
210	〃	274.7	〃	〃	×	
220	〃	301.4	〃	〃	×	
230	〃	329.5	〃	〃	×	
240	〃	358.7	〃	〃	×	
250	〃	389.3	〃	〃	×	
260	〃	421.0	〃	〃	×	
270	〃	454.0	〃	〃	×	
280	〃	488.3	〃	〃	×	
290	〃	523.8	〃	〃	×	
300	〃	560.5	〃	〃	×	
310	〃	598.5	〃	〃	×	
320	〃	637.8	〃	〃	×	
350	〃	762.6	〃	〃	×	

×印は計量する寸法です。SUS303 丸棒は材質識別の為両端面にピンクのスプレーをしております。