

# 5 0 5 2 切 断 板

(切 断 売 り)

JIS 規格名及記号 H4000 A5052P  
 配 合 (%) Cu0.10以下 Si0.25以下  
 Fe0.40以下 Mn0.10以下  
 Mg2.2~2.8 Zn0.10以下  
 Cr0.15~0.35  
 Al残部  
 質 比 別 H112  
 重 2.69

(単位m/m)

厚 公 差	0.7を超え	1.1以下	±0.10
	1.1 "	3.6 "	±0.13
	3.6 "	4.5 "	±0.20
	4.5 "	5.0 "	±0.25
	5.0 "	6.5 "	±0.28
	6.5 "	8.0 "	±0.33
	8.0 "	11 "	±0.48
	11 "	16 "	±0.65
	16 "	22 "	±0.80
	22 "	29 "	±0.90
	29 "	35 "	±1.0
	35 "	40 "	±1.1
	40 "	50 "	±1.3
	50 "	55 "	±1.5
	55 "	70 "	±1.9
	70 "	75 "	±2.3
75 "	200 "	±2.8	
250 "	300 "	0~+6.0	
350 "		0~+7.0	

厚 さ mm	元 板		一 枚 重 量 kg	備 考
	幅 mm	長さ mm		
1.0	1,000	2,000	5.380	} H34
1.5	"	"	8.070	
2.0	"	"	10.760	
3.0	1,250	2,500	25.218	
4.0	"	"	33.625	
5.0	"	"	42.031	
6.0	"	"	50.437	} H112
7.0	1,000	2,000	37.660	
8.0	1,250	2,500	67.250	
9.0	1,000	2,000	48.420	
10.0	1,250	2,500	84.062	
12.0	"	"	100.875	
15.0	"	"	126.093	
16.0	"	"	134.500	
18.0	"	"	151.312	
20.0	"	"	138.125	
22.0	1,000	2,000	118.360	
25.0	1,250	2,500	210.156	
28.0	"	"	235.375	
30.0	"	"	252.187	
32.0	"	"	269.000	
35.0	"	"	294.218	
36.0	"	"	302.625	
40.0	"	"	336.250	

一口メモ 当社切断品は5ミリまではH34です。尚、保護シートご注文の場合は板厚10ミリを超える場合はすべてS.P.V(塩ビ、乳白色)となります。  
 また、上記製品は切断はもちろんですが元板でも販売致します。

