

ステンレス板 SUS 304 L (No.1) 切断板

(切 断 売 り)

JIS 規格名及記号 G4304 SUS304L-HP
 配 合 (%) Ni 9.0~13.0 Cr18.00~20.0
 C 0.03以下 Si1.0以下 Mn2.0以下
 P0.045以下 S0.03以下
 仕 上 げ No.1
 比 重 7.93

(単位m/m)

板 厚 公 差	2.5 以上3.15未満	±0.35
	3.15 " 4.0 "	±0.40
	4.0 " 5.0 "	±0.45
	5.0 " 6.0 "	±0.50
	6.0 " 8.0 "	±0.60
	8.0 " 10.0 "	±0.65

厚 さ mm	元 板		1 枚 重 量 kg	備 考
	幅 mm	長さ mm		
3.0	1,525	3,050	110.70	
4.0	"	"	147.50	
5.0	"	"	184.42	
6.0	"	"	221.30	
7.0	"	"	258.19	
8.0	"	"	295.10	
9.0	"	"	331.96	
10.0	"	"	368.84	
12.0	"	"	442.61	
14.0	"	"	516.38	
15.0	"	"	553.27	
16.0	"	"	590.19	
18.0	"	"	663.92	
19.0	"	"	700.80	
20.0	"	"	737.69	
22.0	"	"	811.46	
25.0	"	"	922.11	
28.0	"	"	1,032.76	
30.0	"	"	1,106.53	
32.0	"	"	1,180.30	
35.0	"	"	1,290.95	
38.0	"	"	1,401.61	
40.0	"	"	1,475.68	
42.0	"	"	1,549.15	
45.0	"	"	1,659.80	
50.0	"	"	1,844.22	
55.0	"	"	2,028.64	
60.0	"	"	2,213.06	
65.0	"	"	2,397.49	
70.0	"	"	2,581.91	
75.0	"	"	2,766.33	
80.0	"	"	2,950.75	
85.0	"	"	3,135.18	
90.0	"	"	3,319.60	
95.0	"	"	3,504.02	
100.0	"	"	3,688.44	

一口メモ SUS304Lとは、極低炭素なのでSUS304に比べて溶接による粒界腐食を防止できる。用途、石油化学工業、各種化学 etc.