

ステンレス板 SUS 316 L (No.1) 切断板

(単位m/m)

(切断売り)
(一部定尺売り)

JIS 規格名及記号 G4304 SUS316L-HP
 配合 (%) Ni 12.0~15.0 Cr 16.0~18.0
 Mo 2.0~3.0 C 0.03以下 Si 1.0以下
 Mn 2.0以下 P 0.045以下 S 0.03以下
 仕上 げ No.1
 比 重 7.93

板 厚 公 差	2.5 以上 3.15未満	±0.35
	3.15 " 4.0 "	±0.40
	4.0 " 5.0 "	±0.45
	5.0 " 6.0 "	±0.50
	6.0 " 8.0 "	±0.60
	8.0 " 10.0 "	±0.65
	10.0 " 15.0 "	±0.70
	16.0 " 22.0 "	±0.80
	25.0 " 30.0 "	±0.80
	40.0 " 60.0 "	±1.20

厚 さ mm	元 板		1 枚 重 量 kg	備 考
	幅 mm	長さ mm		
0.3	1,525	3,050	11.13	
0.5	"	"	18.45	
0.8	"	"	29.69	
1.0	"	"	37.12	
1.2	"	"	44.54	
1.5	"	"	55.68	
2.0	"	"	74.23	
3.0	"	"	111.40	
4.0	"	"	148.50	
5.0	"	"	185.58	
6.0	"	"	222.70	
8.0	"	"	297.00	
9.0	"	"	334.05	
10.0	"	"	371.17	
12.0	"	"	445.40	
14.0	"	"	519.64	
15.0	"	"	556.75	
16.0	"	"	593.87	
18.0	"	"	668.11	
19.0	"	"	705.22	
20.0	"	"	742.34	
22.0	"	"	816.57	
25.0	"	"	927.92	
28.0	"	"	1,039.28	
30.0	"	"	1,113.51	

一口メモ SUS 316Lは SUS 316の炭素含有量を低くした鋼種で一般耐食性は SUS 316 と同等であるが、溶接のまま耐粒界腐食性を必要とするところに用いる。用途は SUS 316 と同じ。

ステンレス板SUS316L (No.1) 切断板
(切断売り)

厚さ mm	元板		1枚重量 kg	備考
	幅 mm	長さ mm		
32.0	〃	〃	1,187.74	
35.0	〃	〃	1,299.09	
38.0	〃	〃	1,410.45	
40.0	〃	〃	1,484.68	
45.0	〃	〃	1,670.26	
50.0	〃	〃	1,855.85	
55.0	〃	〃	2,041.43	
60.0	〃	〃	2,227.02	
65.0	〃	〃	2,412.60	
70.0	〃	〃	2,598.19	
75.0	〃	〃	2,783.77	
80.0	〃	〃	2,969.36	
85.0	〃	〃	3,154.94	
90.0	〃	〃	3,340.53	
95.0	〃	〃	3,526.11	
100.0	〃	〃	3,711.70	