

ステンレス平角棒 SUS 304 (コールド & HL)

(切 断 売 り)

(単位: m/m)

JIS 規格名及記号 G4318 SUS304-CB

配 合 (%) Ni8.00~10.50 Cr18.00~20.00

C0.08 以下 Si1.00以下

Mn2.00以下 P0.045以下 S0.03以下

Fe残

仕 上 げ コールド (冷間引抜品)、HL

比 重 7.93

厚 さ 及 び 巾 公 差	3以下	+0 -0.14
	3を超え 6 "	+0 -0.18
	6 " 10 "	+0 -0.22
	10 " 18 "	+0 -0.27
	18 " 30 "	+0 -0.33
	30 " 50 "	+0 -0.39
	50 " 80 "	+0 -0.46
	80 " 120 "	+0 -0.54

厚 さ mm	幅 mm	長 さ mm	1 枚 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
2.0	6.0	2,000	0.19	○	可	
2.0	8.0	"	0.25	○	"	
2.0	9.0	"	0.29	○	"	
2.0	10.0	4,000	0.64	○	"	
2.0	12.0	"	0.76	○	"	
2.0	15.0	"	0.95	○	"	
2.0	20.0	"	1.27	○	"	
2.0	25.0	"	1.59	○	"	
2.0	30.0	"	1.90	○	"	
2.0	32.0	"	2.03	○	"	
2.0	40.0	"	2.54	○	"	
2.0	50.0	"	3.17	○	"	
3.0	6.0	"	0.429	○	"	
3.0	8.0	"	0.571	○	"	
3.0	9.0	"	0.856	○	"	
3.0	10.0	"	0.95	○	"	
3.0	12.0	"	1.14	○	"	
3.0	13.0	"	1.24	○	"	
3.0	15.0	"	1.43	○	"	
3.0	16.0	"	1.53	○	"	
3.0	19.0	"	1.81	○	"	
3.0	20.0	"	1.90	○	"	
3.0	22.0	"	2.09	○	"	
3.0	25.0	"	2.38	○	"	
3.0	30.0	"	2.86	○	"	
3.0	32.0	"	3.04	○	"	
3.0	35.0	"	3.33	○	"	
3.0	38.0	"	3.62	○	"	

○印は無計量採用寸法です。

一口メモ ステンレスと他材料との特性比較

亜鉛鉄板やアルミに比べて高温に強く耐火性にすぐれています。

材質識別の為両端面に黄色のスプレーをしております。

備 考 ・2×6~6×100 サービス研磨品 ・8×10~35×100 スキンパス仕上げ

ステンレス平角棒 SUS 304 (コールド&HL)

(切断売り)

厚さ mm	幅 mm	長さ mm	1本重量 kg	無計量 採用	切断 可否	備考
3.0	40.0	4,000	3.81	○	可	
3.0	42.0	"	4.00	○	"	
3.0	45.0	"	4.28	○	"	
3.0	48.0	"	4.57	○	"	
3.0	50.0	"	4.76	○	"	
3.0	60.0	"	5.71	○	"	
3.0	65.0	"	6.20	○	"	
3.0	75.0	"	7.14	○	"	
3.0	100.0	"	9.52	○	"	
3.0	110.0	"	10.5	○	"	
3.0	120.0	"	11.4	○	"	
3.0	125.0	"	11.9	○	"	
3.0	130.0	"	12.4	○	"	
3.0	140.0	"	13.3	○	"	
3.0	150.0	"	14.3	○	"	
4.0	9.0	"	1.14	○	"	
4.0	10.0	"	1.27	○	"	
4.0	11.0	"	1.40	○	"	
4.0	13.0	"	1.65	○	"	
4.0	15.0	"	1.90	○	"	
4.0	16.0	"	2.03	○	"	
4.0	19.0	"	2.41	○	"	
4.0	20.0	"	2.54	○	"	
4.0	22.0	"	2.79	○	"	
4.0	25.0	"	3.17	○	"	
4.0	30.0	"	3.81	○	"	
4.0	32.0	"	4.08	○	"	
4.0	35.0	"	4.44	○	"	
4.0	38.0	"	4.84	○	"	
4.0	40.0	"	5.08	○	"	
4.0	45.0	"	5.71	○	"	
4.0	50.0	"	6.38	○	"	
4.0	60.0	"	7.61	○	"	
4.0	65.0	"	8.24	○	"	
4.0	75.0	"	9.52	○	"	
4.0	90.0	"	11.42	○	"	
4.0	100.0	"	12.70	○	"	
5.0	8.0	"	1.27	○	"	
5.0	9.0	"	1.43	○	"	
5.0	10.0	"	1.59	○	"	
5.0	12.0	"	1.90	○	"	
5.0	13.0	"	2.06	○	"	
5.0	15.0	"	2.38	○	"	
5.0	16.0	"	2.54	○	"	
5.0	19.0	"	3.01	○	"	
5.0	20.0	"	3.17	○	"	
5.0	22.0	"	3.49	○	"	
5.0	25.0	"	3.96	○	"	

○印は無計量採用寸法です。

一口メモ ステンレスと他材料との特性比較

亜鉛鉄板やアルミに比べて高温に強く耐火性にすぐれています。

材質識別の為両端面に黄色のスプレーをしております。

備考 ・ 2×6～6×100 サービス研磨品 ・ 8×10～35×100 スキンパス仕上げ

ステンレス平角棒 S U S 3 0 4 (コールド & H L)

(切 断 売 り)

厚 さ mm	幅 mm	長 さ mm	1 本 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
5.0	30.0	4,000	4.76	○	可	
5.0	32.0	"	5.08	○	"	
5.0	34.0	"	5.39	○	"	
5.0	35.0	"	5.56	○	"	
5.0	38.0	"	6.04	○	"	
5.0	40.0	"	6.36	○	"	
5.0	50.0	"	7.92	○	"	
5.0	60.0	"	9.52	○	"	
5.0	65.0	"	10.30	○	"	
5.0	75.0	"	11.90	○	"	
5.0	90.0	"	14.3	○	"	
5.0	100.0	"	15.90	○	"	
5.0	130.0	"	20.6	○	"	
5.0	150.0	"	23.8	○	"	
6.0	9.0	"	1.71	○	"	
6.0	10.0	"	1.90	○	"	
6.0	12.0	"	2.28	○	"	
6.0	13.0	"	2.48	○	"	
6.0	15.0	"	2.86	○	"	
6.0	16.0	"	3.04	○	"	
6.0	18.0	"	3.42	○	"	
6.0	19.0	"	3.62	○	"	
6.0	20.0	"	3.81	○	"	
6.0	22.0	"	4.20	○	"	
6.0	25.0	"	4.76	○	"	
6.0	30.0	"	5.72	○	"	
6.0	32.0	"	6.08	○	"	
6.0	35.0	"	6.66	○	"	
6.0	38.0	"	7.24	○	"	
6.0	40.0	"	7.60	○	"	
6.0	42.0	"	7.99	○	"	
6.0	45.0	"	8.56	○	"	
6.0	48.0	"	9.14	○	"	
6.0	50.0	"	9.52	○	"	
6.0	60.0	"	11.42	○	"	
6.0	65.0	"	12.40	○	"	
6.0	70.0	"	13.32	○	"	
6.0	75.0	"	14.30	○	"	

○印は無計量採用寸法です。

一口メモ ステンレスと他材料との特性比較

亜鉛鉄板に比べて強度が大きいので切断や曲げ加工により力が必要ですが、適当な治具工具を使用すれば容易に加工できます。材質識別の為両端面に黄色のスプレーをしております。

ステンレス平角棒 S U S 3 0 4 (コールド & H L)

(切 断 売 り)

厚 さ mm	幅 mm	長 さ mm	1 本 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
6.0	90.0	4,000	17.13	○	可	
6.0	100.0	"	19.00	○	"	
6.0	110.0	"	20.94	○	"	
6.0	120.0	"	22.84	○	"	
6.0	125.0	"	23.79	○	"	
6.0	130.0	"	24.74	○	"	
6.0	140.0	"	26.64	○	"	
6.0	150.0	"	28.55	○	"	
8.0	10.0	"	2.54	○	"	
8.0	16.0	"	4.06	○	"	
8.0	32.0	"	8.12	○	"	
8.0	38.0	"	9.64	○	"	
8.0	50.0	"	12.70	○	"	
9.0	13.0	"	3.71	○	"	
9.0	15.0	"	4.28	○	"	
9.0	16.0	"	4.57	○	"	
9.0	19.0	"	5.44	○	"	
9.0	20.0	"	5.72	○	"	
9.0	22.0	"	6.28	○	"	
9.0	25.0	"	7.12	○	"	
9.0	30.0	"	8.56	○	"	
9.0	32.0	"	9.12	○	"	
9.0	38.0	"	10.80	○	"	
9.0	40.0	"	11.40	○	"	
9.0	50.0	"	14.30	○	"	
9.0	60.0	"	17.13	○	"	
9.0	65.0	"	18.60	○	"	
9.0	75.0	"	21.40	○	"	
9.0	90.0	"	25.69	○	"	
9.0	100.0	"	28.60	○	"	
9.0	125.0	"	35.70	○	"	
9.0	150.0	"	42.80	○	"	
9.0	200.0	"	57.10	○	"	
9.0	250.0	"	71.40	○	"	
9.0	300.0	"	85.60	○	"	
10.0	15.0	"	4.76	○	"	
10.0	19.0	"	6.04	○	"	
10.0	20.0	"	6.36	○	"	

○印は無計量採用寸法です。

一口メモ ステンレスと他材料との特性比較

熱膨張率がアルミり少ないので長尺屋根などに用いた時有利です。又熱伝導率が小であるから保温性が良く浴槽用などに絶好です。

材質識別の為両端面に黄色のスプレーをしています。

ステンレス平角棒 S U S 3 0 4 (コールド & H L)

(切 断 売 り)

厚 さ mm	幅 mm	長 さ mm	1 本 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
10.0	25.0	4,000	7.92	○	可	
10.0	30.0	"	9.52	○	"	
10.0	32.0	"	10.20	○	"	
10.0	38.0	"	12.00	○	"	
10.0	40.0	"	12.69	○	"	
10.0	50.0	"	15.90	○	"	
10.0	65.0	"	20.62	○	"	
10.0	75.0	"	23.85	○	"	
10.0	100.0	"	31.76	○	"	
10.0	125.0	"	39.65	○	"	
10.0	150.0	"	47.58	○	"	
10.0	200.0	"	63.44	○	"	
10.0	250.0	"	79.30	○	"	
10.0	300.0	"	95.16	○	"	
12.0	14.0	"	5.33	○	"	
12.0	16.0	"	6.10	○	"	
12.0	19.0	"	7.24	○	"	
12.0	20.0	"	7.60	○	"	
12.0	25.0	"	9.52	○	"	
12.0	30.0	"	11.40	○	"	
12.0	32.0	"	12.20	○	"	
12.0	35.0	"	13.32	○	"	
12.0	38.0	"	14.50	○	"	
12.0	40.0	"	15.23	○	"	
12.0	50.0	"	19.00	○	"	
12.0	65.0	"	24.80	○	"	
12.0	75.0	"	28.60	○	"	
12.0	90.0	"	34.30	○	"	
12.0	100.0	"	38.10	○	"	
12.0	125.0	"	47.60	○	"	
12.0	150.0	"	57.00	○	"	
12.0	200.0	"	76.10	○	"	
12.0	250.0	"	95.20	○	"	
12.0	300.0	"	114.20	○	"	
16.0	19.0	"	9.64	○	"	
16.0	20.0	"	10.15	○	"	
16.0	25.0	"	12.70	○	"	
16.0	32.0	"	16.20	○	"	

○印は無計量採用寸法です。×印は計量する寸法です。

一口メモ SUS304 コールド大型平角棒はプラズマ溶断不要、機械加工不要の大型平角棒で、最大30×100迄切断販売致します。是非一度御使用ください。プラズマ溶断ものと較べものになりません。

材質識別の為両端面に黄色のスプレーをしています。

ステンレス平角棒 S U S 3 0 4 (コールド & H L)

(切 断 売 り)

厚 さ mm	幅 mm	長 さ mm	1 本 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
16.0	38.0	4,000	19.30	○	可	
16.0	40.0	"	20.30	○	"	
16.0	50.0	"	25.40	○	"	
16.0	65.0	"	33.00	○	"	
16.0	75.0	"	38.10	○	"	
16.0	100.0	"	50.80	○	"	
16.0	125.0	"	63.40	○	"	
16.0	150.0	"	76.10	○	"	
16.0	200.0	"	101.50	×	"	
16.0	250.0	"	126.90	×	"	
16.0	300.0	"	152.30	×	"	
19.0	25.0	"	15.07	○	"	
19.0	32.0	"	19.30	○	"	
19.0	38.0	"	22.90	○	"	
19.0	50.0	"	30.10	○	"	
19.0	65.0	"	39.20	○	"	
19.0	75.0	"	45.20	○	"	
19.0	100.0	"	60.30	○	"	
19.0	125.0	"	75.30	○	"	
19.0	150.0	"	90.40	○	"	
19.0	200.0	"	120.50	×	"	
19.0	250.0	"	150.70	×	"	
19.0	300.0	"	180.80	×	"	
22.0	32.0	"	22.30	○	"	
22.0	38.0	"	26.50	○	"	
22.0	50.0	"	34.90	○	"	
22.0	65.0	"	45.40	○	"	
22.0	75.0	"	52.30	○	"	
22.0	100.0	"	69.80	○	"	
25.0	32.0	"	25.40	○	"	
25.0	38.0	"	30.10	○	"	
25.0	50.0	"	39.60	○	"	
25.0	65.0	"	51.60	○	"	
25.0	75.0	"	59.50	○	"	
25.0	100.0	"	79.30	○	"	
25.0	125.0	"	99.13	○	"	

○印は無計量採用寸法です。×印は計量する寸法です。

一口メモ SUS304 コールド大型平角棒はプラズマ溶断不要、機械加工不要の大型平角棒で、最大30×100迄切断販売致します。是非一度御使用ください。プラズマ溶断ものと較べものになりません。

材質識別の為両端面に黄色のスプレーをしています。

ステンレス平角棒 S U S 3 0 4 (コールド & H L) (切 断 売 り)

厚 さ mm	幅 mm	長 さ mm	1 本 重 量 kg	無 計 量 採 用	切 断 可 否	備 考
30.0	50.0	"	47.6	×	"	
30.0	55.0	"	52.4	×	"	
30.0	65.0	"	62.0	×	"	
30.0	75.0	"	71.2	×	"	
30.0	100.0	"	95.2	×	"	
35.0	50.0	"	55.51	○	"	
35.0	65.0	"	72.16	○	"	
35.0	75.0	"	82.27	○	"	
35.0	100.0	"	111.02	○	"	

○印は無計量採用寸法です。×印は計量する寸法です。

一口メモ S U S 304 コールド大型平角棒はプラズマ溶断不要、機械加工不要の大型平角棒で、最大30×100迄切断販売致します。是非一度御使用ください。プラズマ溶断ものと較べものになりません。
材質識別の為両端面に黄色のスプレーをしております。