

真中板 (メーター板)

(定尺売り、切断は相談下さい)

(単位m/m)

JIS 規格名及記号 H3100 C2801P
 旧JIS 規格名及記号 P3201 BSP3 真中板 3種
 配合 (%) Cu59.0~62.0 Pb0.10以下
 Fe 0.07 以下 Zn残部
 質 別 1/4 H
 比 重 8.43

板 厚 公 差	0.5 以下	±0.09
	0.5を超え 0.8 "	±0.12
	0.8 " 1.2 "	±0.15
	1.2 " 2 "	±0.18
	2 " 3.2 "	±0.20
	3.2 " 5 "	±0.25
	5 " 8 "	±0.30
	8 " 12 "	±0.35

厚 さ mm	幅 mm	長 さ mm	1 枚 重 量 kg	無 計 量 採 用	備 考
0.5	1,000	2,000	8.430	○	
0.6	"	"	10.116	○	
0.7	"	"	11.802	○	
0.8	"	"	13.488	○	
1.0	"	"	16.860	○	
1.2	"	"	20.232	○	
1.5	"	"	25.290	○	
1.6	"	"	26.976	○	
2.0	"	"	33.720	○	
2.3	"	"	38.778	○	
2.5	"	"	42.150	○	
3.0	"	"	50.580	○	
3.2	"	"	53.952	○	
4.0	"	"	67.440	○	
5.0	"	"	84.300	○	
6.0	"	"	101.160	×	
7.0	"	"	118.020	×	
8.0	"	"	134.880	×	
9.0	"	"	151.740	×	
10.0	"	"	177.800	×	

○印は無計量採用寸法です。×印は計量する寸法です。

一口メモ 真中2種は銅(65%割)亜鉛(35%割)の配合で絞り加工性が良くカメラ魔法ビン等に使われます。